Hydel Laboratories (P) Ltd.

Plot No. 2/20, Sec - 2, Rajender Nagar, Sahibabad, Ghaziabad 201005
0120-4125559, 9319391840 info.hydellaboratories@gmail.com
support@hydellabs.com **Website:** www.hydellabs.com

An ISO:9001:2015, ISO:14001:2015, ISO:45001:2018 Certified Laboratory

TEST REPORT

Issued To:	**Vibgyor Sunrise India Pvt Ltd** Near surji wedding point padampur motadhak kotdwar Pauri Garhwal Uttarakhand Pin code 246149	**Report No:**	20260825GEN-07
		Reporting Date:	02.09.2026
Description:	Fabric	**Sample Received On:**	25.08.2026
Sample Qty:	2 Mtr.	**Analysis Start Date:**	25.08.2026
Sampled By:	Customer	**Analysis End Date:**	02.09.2026
		Temp.:	25±5°C
			Page No.: 01 of 01

TEST RESULT

S. No.	Test Parameters	Unit	Result	Test Method
1.	pH Value	-	7.42	IS 1390: 2022
2.	Shrinkage			
(i)	Warp Direction	%	-1.8	IS 2977 :2026
(ii)	Weft Direction	%	-1.1	IS 2977 :2026
3.	Color Fastness			
(i)	Washing	-	4	IS/ISO 105-C06
(ii)	Rubbing			
(a)	Dry	-	4-5	IS/ISO 105-X12
(b)	Wet		4	IS/ISO 105-X12
(iii)	Perspiration			
(a)	Acid		4	IS/ISO 105-E04
(b)	Alkali		4	IS/ISO 105-E04
4.	Pilling Test	-	4	IS 10971
5.	Fiber Composition			
(i)	Cotton	%	65.4	IS 3416 (P-1): 1988
(ii)	Polyester	%	34.6	IS 3416 (P-1): 1988
6.	Tear Resistance			
(i)	Warp Direction	N	18	IS 6489 (P-2): 2011
(ii)	Weft Direction	N	16	IS 6489 (P-2): 2011
7.	Tensile Strength			
(i)	Warp Direction	N	319	IS 1969 (P-1): 2018
(ii)	Weft Direction	N	298	IS 1969 (P-1): 2018
8.	GSM	g/m^2	116	IS 1964 :2025

End of Report

बिना होलोग्राम के रिपोर्ट मान्य नही है

Reviewed By

HYDEL LABORATORIES Akhilesh Pratap Singh Technical Manager GHAZIABAD

Authorized Signatory

Note:-
- The result indicated only refer to the tested samples and listed parameters and do not endorse any product.
- Total liability of the laboratory is limited to the invoiced amount.
- This certificate shall not be reproduced wholly or in part without prior written consent of the laboratory.
- Samples received shall be destroyed after four weeks from the date or issue of the certificate unless specified otherwise.
- This certificate shall not be used in any advertising media or as evidence in the Court of Low without prior written consent of the laboratory.

Hydel Laboratories (P) Ltd.

Plot No. 2/20, Sec - 2, Rajender Nagar, Sahibabad, Ghaziabad 201005
0120-4125559, 9319391840 info.hydellaboratories@gmail.com
support@hydellabs.com **Website:** www.hydellabs.com

An ISO:9001:2015, ISO:14001:2015, ISO:45001:2018 Certified Laboratory

TEST REPORT

Issued To:	**Vibgyor Sunrise India Pvt Ltd** Near surji wedding point padampur motadhak kotdwar Pauri Garhwal Uttarakhand Pin code 246149	**Report No:**	20260825GEN-08
		Reporting Date:	02.09.2026
		Sample Received On:	25.08.2026
Description:	Fabric	**Analysis Start Date:**	25.08.2026
Sample Qty:	2 Mtr.	**Analysis End Date:**	02.09.2026
Sampled By:	Customer	**Temp.:**	25±5°C
			Page No.: 01 of 01

TEST RESULT

S. No.	Test Parameters	Unit	Result	Test Method
1.	pH Value	-	6.94	IS 1390: 2022
2.	Shrinkage			
(i)	Warp Direction	%	-0.5	IS 2977 :2026
(ii)	Weft Direction	%	-0.3	IS 2977 :2026
3.	Color Fastness			
(i)	Washing	-	4-5 grade	IS/ISO 105-C10
(ii)	Rubbing			
(a)	Dry	-	4-5	IS/ISO 105-X12
(b)	Wet		4	IS/ISO 105-X12
(iii)	Perspiration			
(a)	Acid		4-5	IS/ISO 105-E04
(b)	Alkali		4-5	IS/ISO 105-E04
4.	Pilling Test	-	5	IS 10971
5.	Fiber Composition			
(i)	Polyester	%	81.6	IS 3416 (P-1): 1988
(ii)	Viscose	%	18.4	IS 3416 (P-1): 1988
6.	Tear Resistance			
(i)	Warp Direction	N	44	IS 6489 (P-2): 2011
(ii)	Weft Direction	N	37	IS 6489 (P-2): 2011
7.	Tensile Strength			
(i)	Warp Direction	N	738	IS 1969 (P-1): 2018
(ii)	Weft Direction	N	616	IS 1969 (P-1): 2018
8.	GSM	g/m^2	244.5	IS 1964 :2025

End of Report

Reviewed By

बिना होलोग्राम के रिपोर्ट मान्य नही है

HYDEL LABORATORIES GHAZIABAD
Akhilesh Pratap Singh Technical Manager

Authorized Signatory

Note:-
- The result indicated only refer to the tested samples and listed parameters and do not endorse any product.
- Total liability of the laboratory is limited to the invoiced amount.
- This certificate shall not be reproduced wholly or in part without prior written consent of the laboratory.
- Samples received shall be destroyed after four weeks from the date or issue of the certificate unless specified otherwise.
- This certificate shall not be used in any advertising media or as evidence in the Court of Low without prior written consent of the laboratory.